





Aurus Regal Interiors Matt, is a high performance emulsion for interior walls with a rich matt finish which brings colours to life. Thoughtfully designed to provide superior performance and application properties, it delivers exceptional flow and levelling with great coverage and extreme hide.

Experience, Aurus Regal Interiors Matt - Thoughtfully designed for a Rich Matt Finish.



FEATURES

*****=

Paint & Primer Low VOC **Rich Matt Anti-Fungal Endures 5 years**

Superior Opacity Excellent Smooth Finish Fast and Easy to Finish **Roller Friendly Paint**

CAUTION

(!)

Do not apply below 10°C or above 45°C

Do not apply if humidity > 90%

Do not over-thin. Use thinned paint within 24 hours

Shake, stir and strain paint before use

In case of eye contact, wash with plenty of water

Tightly close the lid when not in use and store in a cool, dry place

CERTIFICATION



Compliant to VOC requirement for Paints for LEED rated buildings1


Compliant to GRIHA standards for Low VOC²

No Fungal Growth as per ASTM Test D5590:2017³



PREPARATION





- Remove any peeling paint and sand these areas to feather edges smooth with adjacent surfaces
- New plaster or masonry surfaces must be allowed to cure (28 days) before application
- Cured plaster should be hard (non-powdery) and in sound condition
- Growths of fungus, algae or moss should be removed by wire brushing and washing thoroughly with potable water
- In case of areas having excess dampness, please repair the surface before painting
- In case there are structural cracks, please study and repair them with a structural engineer
- Open non-structural cracks in V-groove and fill with cement/crack filler
- Apply cement/acrylic putty (wherever needed) to fill the dents and level the surface
- Sand and smoothen the surface with sand paper no. 320 and wipe clean before paint application

APPLICATION

ROLLER For best results, use a Short Nap Felt Roller DILUTION Dilute Aurus Regal Interiors with 25% clean water

For re-painting^ (Paint & Primer):

STEP 1	FIRST	Aurus	4 hrs
	COAT	REGAL INTERIORS	dry
STEP 2	SECOND	Aurus	4 hrs
	COAT	REGAL INTERIORS	dry

For new masonry surface^:

STEP 1	1 COAT	Wall Primer INTERIORS	3-4 hrs dry
STEP 2	2 COATS	Wall Putty ACRYLIC BASED	6-8 hrs dry
STEP 3	1 COAT	Wall Primer INTERIORS	3-4 hrs dry before re-coat
STEP 4	2 COATS	Aurus REGAL INTERIORS	4 hrs dry before re-coat



PAINT & PRIMER

Aurus Regal Interiors is specially formulated to blend the functions of a primer with the finish coat. Two coats of Aurus Regal Interiors provides a sturdier coat that the conventional 'Primer + 2 Finish coats' system, bringing your vision to life in quick time with less effort.*



ENVIRONMENTAL HEALTH AND SAFETY

- · Use only with adequate ventilation during application and drying
- · Avoid contact with eyes and prolonged or repeated contact with skin
- · Do not breathe spray mist or sanding dust
- · Use dust mask or nose pad during application, sanding and clean up
- Close container after each use
- · Wash thoroughly after handling
- In case of contact with eyes, rinse immediately with plenty of water and seek medical advice
- In case of skin contact, immediately wash skin with soap and plenty of water.
 Get medical attention if irritation develops or persists
- No added Lead, Mercury, Chromium, Arsenic and other heavy metals

POST PAINTING CARE

- · Always remove any wall stains immediately from the walls
- Remove all dirt using a clean cloth or duster. Always remove dirt from top to bottom. This helps in avoiding loose dirt to smudge the walls
- For household stains like pencil, tea, coffee, crayons, turmeric, ketchup, sketch pen etc., use liquid dish wash/mild detergent solution. Use a sponge to remove the stains. Wipe the area with a clean cloth

PRODUCT INFORMATION

White

Colours
Tint Bases

AI-1, AI-3, AI-4, AI-Y, AI-M

KEY DATA

No. of colours

1808 shades

(Ask for Colour**vista** Shade **Panorama** fandeck)

Coverage^

130 - 150 sq.ft./L/2 coats 12 - 13.9 m²/L/2 coats

Drying Time* (30°C @ 60 R/H) Surface Dry - 30 minutes

Recoat - 4 hours

Flash Point

N/A

Sheen Level

2 - 5 units @ 60° GH

Vehicle Type

Acrylic

Thin with

Clean Water (upto 25%)

<20 gms/L

Other Aurus products:

JSW Paints Aurus Range offers high performance emulsions for exterior walls for a beautiful experience of painting spaces.

JSW Paints - Think Beautiful. Every JSW Paints product works to transform beautiful thoughts to reality. Everything about the paint, its application and finish is designed to be the 'Simple-Swift-Sure' way to making homes beautiful.









JSW Paints presents Colour vista Shade Panorama, a splendid collection of 1808 curated shades assembled in tones for every mood. The Colour vista Shade Panorama Fandeck is uniquely designed to easily pick the right colour and choose colour combinations for homes.



Colour*vista* Shade Panorama

FEATURES OF THE INNOVATIVE FANDECK

- 1808 Curated Shades
- Tone Based User-friendly Fandeck
- Easy to Choose Colour Combinations

¹Compliant to LEED (Leadership in Energy & Environmental Design) VOC criteria as per IGBC (Indian Green Building Council) as tested at National Test House, Mumbai. ²Compliant to GRIHA (Green Rating for Integrated Habitat Assessment) Criterion 26 on Low VOC Interior Paints as tested at National Test House, Mumbai. ³No fungal growth when tested as per ASTM D5590: 2017 for 'Determining the Resistance of Paint Films to Fungal Defacement' as tested at Biotech Testing Services, Mumbai.

Version No. 01 (04/2019.)

This information sheet supersedes all previous versions

For feedback/complaints, write to Customer Care Manager, JSW Paint Pvt. Ltd, Jindal Mansion, 5A, Dr. G.Deshmukh Marg, Mumbai 400 026, India or email at ccpaints@jsw.in or call on 1800-121-5797.

- *Drying time and number of coats are dependent on temperature, humidity, surface porosity and film thickness.
- ^Actual coverage may vary from the quoted coverage, due to factors such as method and condition of application and surface roughness and porosity.
- ~VOC Levels as certified by NTH. Meets VOC as per BIS Standard IS 101 (Part 2/Sec 2)/1986 & IS 101 (Part 2/Sec 1)/1988