



# Halõ Exceed MEGA



JSW Paints Halo Exceed Mega is a high performance luxury exterior emulsion with a unique blend of acrylic emulsion and PUD. Engineered to provide outstanding crack bridging and anti-carbonation property, it gives your home ultimate protection in all weather conditions. It is a specially optimised formula that provides long-lasting durability and keeps your home cooler upto 10°C\*.

Halo Exceed Mega Long Lasting Exteriors comes with 15 years of endurance, 15 years of waterproofing and 10 years of Anti-Algal benefits.



POLYURETHANE DISPERSION (PUD)

## TOP COAT PACK SIZES



## BASE COAT PACK SIZES



## GLOSS



## FEATURES

- Low VOC.
- Anti-Fungal.
- Dust Resistant.
- 15 years endurance.
- 15 years waterproofing.
- 10 years anti-algal.
- Enriched with PUD.
- Crack bridging up to 2.5 mm.
- Surface temperature reduction upto 10°C.\*
- Anti Carbonation.
- Colour retention.

## CAUTION

- Do not apply at temperatures below 10°C or if temperature might drop to this level within 4 hours of application or above 45°C.
- Do not apply if humidity > 85%.
- Do not over-thin. Use thinned paint within 24 hours.
- Shake, stir and strain paint before use.
- In case of eye contact, wash with plenty of water.
- Tightly close the lid when not in use and store in a cool dry place.
- Do not keep pails in direct sunlight.
- Base Coat or only one coat of Top Coat should not be kept exposed in monsoon. Complete application before monsoon to be ensured.
- Ensure to use potable water for dilution.


## CERTIFICATION

- Compliant to VOC requirement for paint for LEED rated buildings<sup>1</sup>.
- Crack bridging is carried out in accordance with EN- 1062 Part 7: 2004 - Method A<sup>2</sup>.
- Anti-Carbonation test carried out in accordance with EN- 1062 Part 6: 2002 - Method A<sup>3</sup>.
- No algal growth as per ASTM Test D5589-09 (2013)<sup>4</sup>.
- Anti-fungal.
- UV test results as per inhouse testing on QUV machine.
- Surface Temperature Reduction test is carried out as per ASTM D 4803: 2018.



## SURFACE PREPARATION

- Surfaces to be painted must be clean, dry and free from seepage, leakage, loose old paint, dirt, dust, grease, oil, soap, wax and other impurities.
- Remove any peeling paint and sand in these areas to feather edges smooth with adjacent surfaces.
- Growth of fungus, algae or moss should be removed by wire brushing and wash thoroughly with potable water.
- In case of areas having excess dampness, please repair the surface before painting.
- Please arrest the source of water leakage or seepage in wall before application.
- Do not apply the paint if moisture percentage is more than 15% in substrate.
- Open non-structural cracks in V-groove and fill with cement/crack filler.
- Wipe clean before paint application.
- In case there are structural cracks, please study and repair them with a structural engineer.
- New plaster or masonry surfaces must be allowed to cure for 28 days before application.
- Cured plaster should be hard (non-powdery) and in sound condition.
- Avoid application in rainy season.
- In case of early rain after application and paint wash off, additional coat is recommended.



## APPLICATION

**ROLLER:** For best results, use a Long Nap Felt Roller.

**For Repainting^ (Paint & Primer):**

STEP 1	1 COAT	Halõ Exceed MEGA BASECOAT	4 hours dry Vertical & horizontal surfaces, no dilution, coverage 30-35 sqft/L.
STEP 2	2 COATS	Halõ Exceed MEGA MEGA TOPCOAT	4 hours dry before recoat, vertical surfaces upto 40% dilution, coverage 55-65 sqft/L.

Actual coverage may vary from the quoted coverage due to factors such as method, condition of application, surface roughness and porosity. Please ensure you purchase the appropriate amount of product for the job.  
For horizontal surfaces, one additional coat of Halo Exceed Mega Topcoat is required.

**For New Masonry Surface^:**

STEP 1	1 COAT	Halõ Exceed MEGA BASECOAT	4 hours dry Vertical & horizontal surfaces, 25% dilution, coverage 50 sqft/L.
STEP 2	1 COAT	Halõ Exceed MEGA BASECOAT	4 hours dry before recoat, vertical & horizontal surfaces, no dilution, coverage 40-50 sqft/L.
STEP 3	2 COATS	Halõ Exceed MEGA TOPCOAT	4 hours dry before recoat, vertical surfaces upto 40% dilution, coverage 55-65 sqft/L for 2 coats.

For horizontal surfaces, one additional coat of Halo Exceed Mega Topcoat is required.



## INFORMATION AND CARE

### ENVIRONMENTAL HEALTH AND SAFETY

- Use only with adequate ventilation during application and drying.
- Avoid contact with eyes and prolonged or repeated contact with skin.
- Do not breathe spray mist or sanding dust.
- Use dust mask or nose pad during application, sanding and clean up.
- Close container after each use.
- Wash thoroughly after handling.
- In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
- In case of skin contact, immediately wash skin with soap and plenty of water. Get medical attention if irritation develops or persists.
- No added Lead, Mercury, Chromium, Arsenic and other heavy metals.

### POST PAINTING CARE

- Prevent water stagnation, overgrowth of plants and trees near the painted surface.
- Prevent sharp objects or impact that damage the paint film.
- Ensure proper cleaning of the surface at an interval of 6 months.

## PRODUCT INFORMATION

Colours	White
Tint Bases	HEEM-1, HEEM-2, HEEM-3, HEEM-4

### KEY DATA

No. of colours	1367 shades (Ask for Colourv <sup>ista</sup> Shade <i>Panorama</i> fandeck)
Coverage <sup>^</sup>	55-65 sqft/ltr/2 coats
Drying Time** (30°C @ 60 R/H)	Surface Dry - 30 minutes Recoat - 4 hours
Flash Point	N/A
Sheen Level	17 - 32 units @ 60° GH
Vehicle Type	Acrylic
Thin with	Potable Water (upto 25%)
VOC levels~	<25 gms/L

## Other Halõ products:

JSW Paints Halo Range offers best-in-class emulsions for interior and exterior walls, eco-friendly water-based enamels - Aquaglo for Wood & Metal and fresh range of fragrances for a beautiful experience of painting spaces.

Carefully crafted for a glorious feel. The Halo Fresh range of fragrance additives lends a fresh, new feel that makes a home feel airy, beautiful and as good as new.

JSW Paints - Think Beautiful. Every JSW Paints product works to transform beautiful thoughts to reality. Everything about the paint, its application and finish is designed to be the 'Simple-Swift-Sure' way to making homes beautiful.



MAJESTIC INTERIORS



MAJESTIC INTERIORS



MAJESTIC INTERIORS



FRESH  
MAJESTIC FRAGRANCES



JSW Paints presents Colourv<sup>ista</sup> Shade *Panorama*, a splendid collection of 1808 curated shades assembled in tones for every mood. The Colourv<sup>ista</sup> Shade *Panorama* Fandeck is uniquely designed to easily pick the right colour and choose colour combinations for homes.



Colourv<sup>ista</sup> Shade Panorama

### FEATURES OF THE INNOVATIVE FANDECK

- 1808 curated shades
- Tone-based user-friendly fandeck
- Easy-to-choose colour combinations

<sup>1</sup>Compliant to LEED (Leadership in Energy & Environmental Design) VOC criteria as per IGBC (Indian Green Building Council) as tested at National Test House, Mumbai. <sup>2</sup>Crack Bridging is carried out in accordance with EN- 1062 Part 7: 2004 - Method A. <sup>3</sup>Anti Carbonation test carried out in accordance with EN- 1062 Part 6: 2002 - Method A. <sup>4</sup>No Algal Growth when tested as per ASTM D5589-09 (2013) for determining the resistance of Paint Films to Algae Defacement as tested at Biotech Testing Services, Mumbai.

Version No. 01 (11/2024)

This information sheet supersedes all previous versions.

For feedback/complaints, write to Customer Care Manager at JSW Paints Ltd., Jindal Mansion, 5A, Dr. G. Deshmukh Marg, Mumbai - 400026, India, or email at [ccpaints@jsw.in](mailto:ccpaints@jsw.in) or call on 1800-121-5797

\*The tested product sample for STR certification is white.

\*\*Drying time and number of coats are dependent on temperature, humidity, surface porosity and film thickness.

<sup>^</sup>Actual coverage may vary from the quoted coverage, due to factors such as method and condition of application and surface roughness and porosity.

~VOC Levels as certified by NTH. Meets VOC as per BIS Standard - IS 101 (Part 2/Sec 2)/1986 & IS 101 (Part 2/Sec 1)/1988